

A product of: Unity Creations, LTD.



Interlocking, Unitary, Rubberized Safety Surfacing, Flooring and Pavers.

TURF TOP = ROOF (RUBBER) PAVERS 07 76 00

SALES & MARKETING DEPT:

Unity Surfacing Systems
56 Bloomingdale Rd.
Hicksville, NY. 11801
T: (516) 724-1357
F: (845) 246-1700
E-mail: productinfo@surfacingystems.com
Internet: www.surfacingystems.com

MANUFACTURING PLANT:

Unity Creations, Ltd.
3997 RT 9W (PO Box 9)
Saugerties, NY. 12477
T: (845) 246-2700
F: (845) 246-1700
E-Mail techinfo@surfacingystems.com
Internet: www.surfacingystems.com

**Construction Specification Institute (CSI) and Construction Specifications Canada (CSC) 3-Part Format,
MasterFormat, SectionFormat and PageFormat. (April 2016 Edition)
Section 07 76 00 Roof Pavers**

PART 1: GENERAL

1.1 Section Includes:

Resilient, self-interlocking (with “Button-Lock™ Technology”) unitary, rubberized safety surfacing, flooring and paver products in the tile/mat/block/paver form.

1.2 Related Sections:

Division 7

Sub: 07 32 00 Roof Tiles

Specifically; 07 32 29 Rubber Tiles/Panels

Sub: 07 72 00 Roof Accessories

Specifically: 07 72 43 Roof Walkway Boards

Specifically: 07 72 46 Roof Walkways

Sub: 07 76 00 Roof Pavers

Specifically: 07 76 13 Roof Ballast Pavers

Specifically: 07 76 16 Roof Decking Pavers

Division 9

Sub: 09 30 00 Tiling

Specifically; 09 30 19 Paver Tiling

Division 32

Sub: 32 14 00 Unit Paving

Specifically; 32 14 29 Rubber Paving

Specifically: 32 14 43 Porous Unit Paving

1.3 References:

A.) Applicable Standards:

American Standard for Testing Materials (ASTM)

Consumer Product Safety Commission (CPSC)

American National Standards Institute (ANSI)

Factory Mutual (FM)

B.) ASTM F1292-04 and F355-95 Drop Test

Standard Test Method for Impact Attenuation of Surface Systems Under and Around Playground Equipment.

C.) ASTM C67 Weathering/Aging

Standard Test Method for Weathering and Aging of Surface Systems and Materials.

Standard Test Method for Rubber – Deterioration in an Air Over.

D.) ASTM E108: Class A Fire Test/Flammability

Standard Test Method for Fire Tests of Surface Systems and Materials.

E.) ASTM E108 Class A Fire Test/Flammability - Modified For Roof Coverings:

Modified Test Methods for Fire Tests of Roof Covering Materials.

F.) ASTM E648 Self Extinguishing Fire Test/Flammability

Standard Test Method for Critical Radiant Flux of Floor Covering Systems Using a Radiant Heat Energy Source (NFPA Designation No. 253).

G.) ASTM D2859 Burn Pill

Standard Test Method for the Surface Flammability of Products (Burn Pill Test).

H.) ASTM E303-93 (2013) Skid Resistance

Standard Test Method for Measuring Surface Frictional Properties Using the British Pendulum Tester.

I.) ASTM F1951-99 ADA Accessibility

Standard Specification for Determination of Accessibility of Surface Systems Under and Around Playground Equipment.

J.) ASTM C518-98 Insulation/R-Values

Standard Test Method for Steady-State Thermal Transmission Properties by Means of the Heat Flow Meter Apparatus. Measuring = Insulation/R-Values.

K.) ASTM E903, E891, E1980 Solar Reflectance

Hemispherical Spectral Reflectance and Total Emittance Test. Presents results of spectral reflectance and total emittance of products tested.

- L.) CPSC-CH-E1002-08 Lead Content
LEAD Test - For compliance with US Public Law 110-314 (HR 4040 “Consumer Product Safety Improvement Act of 2008”), lead in accessible substrate materials.
- M.) Water Penetration Test:
For compliance with Sustainable Storm Water Run-off in a testing environment to determine how much water flows through the product based on real world scenarios.
- N.) Leadership in Energy and Environmental Design (LEED):
1.) Criteria development by the United States Green Build Council (USGBC):
a.) Materials and Resources:
Up to 6 points / credits toward LEED certification.
b.) Indoor Environmental Quality:
Up to 1 point / credit toward LEED certification.
- O.) ANSI/FM 4474 Wind Up-Lift
Simulated Wind Up-lift Pull-Force Test Procedure (adhered), to allow design pressure that is estimated to be 277.5 psf. (2:1 Factor of Safety) for systems installed in this manner.
- P.) ASTM D 3161-09 Non-Adhered, Over-Top and at Kick-Plate) Modified for Rubber Pavers
Standard Test Method for Wind Resistance (Fan-Induced) via air velocity of 150 MPH.
- Q.) UL 2218, Class 4 Impact Resistances, 2010.
Standard Test Method for Impact Resistance of Prepared Roof Covering Materials.
- R.) ASTM D 412(13) Tensile Strength, Elongation at Break and Modulus
Standard Test Methods for Vulcanized Rubber and Thermoplastic Elastomers – Tension.
- S.) ASTM D 624 Tear Resistance
Standard Test Method for Tear Strength of Conventional.
- T.) ASTM D 3389 (10) Taber Abrasion Index
Standard Test Method for Walking Surface Based on Abrasion Cycles.
- U.) ASTM D 2240 Durometer Hardness
Standard Test Method for Measuring the “Hardness” of Rubber Elastomers and Plastic.
- V.) ASTM D 1667 Compression Deflection
Standard Test Method for Flexible Cellular Materials.
- W.) ASTM E-831 Coefficient of Thermal Expansion
Standard Test Method for Thermal Expansion of Materials by Thermomechanical Analysis
- X.) ASTM D 3574 Compression Resistance
Standard Test Method for Flexible Cellular Materials.
- Y.) ASTM D 3676 (13) and D 395 Mass and Density Per Unit Area, including Compression Set
Standard Specification for Rubber by way of Mass, Density and Recovery Per Area.
- Z.) Tensile Strength at Interlocking Joint
For compliance with Pull Force in a testing environment to determine how much pressure it takes to unlock the interlocking joints based on real world scenarios.

1.4 Submittals:

A.) General:

- 1.) Submit listed submittals in accordance with Conditions of the Contract and Division pertaining to Submittal Procedures Section.

B.) Product Data:

- 1.) Submit manufacturer's product data, specifications, detailed drawings and installation Instructions, as well as manufacturer's maintenance and cleaning instructions.

C.) Verification Samples:

- 1.) Submit manufacturer's standard verification samples of 4"X4" minimum, with the PT-55P Turf material on top. Two of the submitted samples must show the male/female self-interlocking connection (with "Button-Lock™ Technology").

D.) Manufacturers Project References:

- 1.) Submit reference list of at least 20 years of projects on all sizes, types and scopes.
- 2.) Include project name, location and contact person of three (3) projects that are similar in size, type and scope as specified herein.

E.) Installer's Project References:

- 1.) Submit a copy of manufacturers issued installation warranty certification.
- 2.) Installers must have 5 years' experience with projects of similar scope & complexity.

F.) Closeout Submittals: Submit the following:

- 1.) Warranty documents as specified herein.
- 2.) Repair & Maintenance documents as issued by the manufacturer.
- 3.) Photographs of completed installation, with close-up shots of cut tiles.
- 4.) Submit listed "Closeouts" in accordance with Conditions of the Contract and Division pertaining to Closeout Procedures Section.

G.) Approvals:

- 1.) Contact manufacturer for information on approvals by major owners, agencies, architects, engineers, municipalities and other industry entities.

H.) Environmental Considerations:

- 1.) These resilient, rubberized safety surfacing flooring and paver products in the tile/mat/block/paver form makes extensive use of clean recycled tire rubber and other recycled rubber products as a major component of its operation that are sourced/ recycled in the United States of America.

I.) Testing Data Results:

- 1.) Submit certified test reports from qualified independent testing agency indicating results of the following testing:

a.) Applicable Standards for Rubber Tile:

- b.) Impact Attenuation (ASTM F1292-04 & F355.95) – Based on thickness used.
- c.) Weathering/Aging (ASTM C67, D573 & F1292-04)
- d.) Flammability/Fire Test For Rubber Portion (ASTM E108)
- e.) Flammability For Rubber Portion (ASTM E108 Modified for roof covers)
- f.) Flammability For Rubber Portion (ASTM E648)

- g.) Flammability/Burn Pill Test (ASTM2859)
- h.) Skid Resistance (ASTM E303-93 / 2013)
- i.) ADA Accessibility (ASTM F1951-99)
- j.) R-Value, Thermal Conductivity (ASTM C518-98)
- k.) Reflectance/SRI and Emittance (ASTM E903, E891, E1980)
- l.) Lead In Materials/Children's Products (CPSC-CH-E1002-08)
- m.) Water Penetration Test (Sustainable Storm Water MGT/Run-off)
- n.) Leadership in Energy and Environmental Design (LEED)
- o.) Pull Force Test (ANSI/FM 4474 Approval, Appendix B)
- p.) Wind Resistance (ASTM D3161-09)
- q.) Class 4 Impact Resistance (UL 2218, 2010)
- r.) Tensile Strength, Elongation at Break and Modulus (ASTM D 412)
- s.) Tear Resistance (ASTM 624)
- t.) Taber Abrasion Index (ASTM D3389)
- u.) Durometer Hardness (ASTM 2240)
- v.) Compression Deflection (ASTM 1677)
- w.) Coefficient of Thermal Expansion (ASTM 831)
- x.) Compression Resistance (ASTM 3574)
- y.) Mass & Density (ASTM 3676) with Compression Set (ASTM D395)
- z.) Tensile Strength at Interlocking Joint (Pull Force)

- aa.) Applicable Standards for Turf Material:
- bb.) Fiber ID; Melt Point (ASTM D7138)
- cc.) Yarn Denier (ASTM D 1577-07)
- dd.) Average Yard Filament Width (ASTM D 3218 07)
- ee.) Average Yard Filament Thickness (ASTM D 3218 07)
- ff.) Total Lead Content Digested by 3052 (ASTM F 2765/EPA 3052, 6010)
- gg.) Aver. Weight: Total, Pile Yarn, Prim. and 2nd Backing (ASTM D 5048-10e1)
- hh.) Pile Height Agility, Multi, Pet Play (ASTM D 5823-19)
- ii.) Average Stitch Count and Gauge (ASTM D 57930 18)
- jj.) Average Total Bind Strength (ASTM 1335-17e1)
- kk.) Average Grab Tear – Length, Mid and Width, CMD (ASTM D 5034-09)
- ll.) Average Pill Flammability (ASTM D 2859-16)
- mm.) Average Abrasive Index (ASTM F 1015-04)
- nn.) Average Drainage Capacity (ASTM F 1551, DIN 18-035)
- oo.) Average ADA Wheelchair Accessibility (ASTM F-1951 -14)

1.5 Quality Assurance/Control:

- A.) Manufacturers Qualifications: Manufacturer shall meet a minimum of one (1) of the following two (2) requirements:
 - 1.) Consistently engaged in manufacturing of self-interlocking rubber tiles/mats/blocks/pavers of similar type that is specified, with a minimum of fifteen (15) years of experience under the same business name and EIN (Employer Identification Number)
 - 2.) Furnished/Supplied a minimum of ten-million (10,000,000) square feet of self-interlocking rubber tiles/mats/blocks/pavers of similar type that is specified.

- B.) Installers Qualifications:
 - 1.) Installers must have 5 years' experience with projects of similar scope & complexity.
 - 2.) Certificate of qualifications from the product installer verified by manufacturer.

1.6 Delivery, Storage and Handling:

A.) Delivery:

- 1.) All materials shall be delivered in good condition in its original unopened packages, bound and shrink wrapped with all labels intact clearly identifying manufacturer, product series/name, color and type.

B.) Storage:

- 1.) All materials and accessory items shall be protected from weather; and shall be stored at temperatures of 50 degrees Fahrenheit (10 degrees C) and rising for 24-hours min.
- 2.) Protect all materials and accessory items from direct sunlight before and during installations.

C.) Handling:

- 1.) Protect all materials and accessory items during handling and installation to prevent unnecessary damage.

1.7 Environmental Requirements:

A.) Tile and Air Temperatures:

- 1.) Ensure both the turf tile and air temperature is a minimum of 50 degrees Fahrenheit (10 degrees C) and rising for 24-hours min.
- 2.) Consult with manufacturer's installation guide/manual for installations in conditions less than 50 degrees Fahrenheit (10 degrees C) and/or greater than 85 degrees Fahrenheit (29 degrees C).
- 3.) Ensure that turf-top tiles are not installed in a manner where direct sunlight is projected from any highly reflective or shiny surfaces onto the turf material for prolonged periods of time as it can create a magnifying effect and melt the turf material.

1.8 Warranty Information:

A.) Manufacturer's Warranty:

- 1.) Submit, for Owner's acceptance, manufacturer's standard warranty document executed by authorized company official. Manufacturer's warranty is in addition to, and not a limitation of, other rights Owner may have under contract documents.

B.) Material Warranty Period:

- 1.) Standard Five (5) Years from date of product shipment; or a Ten (10) Year Pro-rated Warranty from date of product shipment shall be selected prior to ordering. A default Five (5) Year Pro-rated Warranty shall be issued if no other warranty is selected prior to ordering.

C.) Installation/Workmanship Warranty Period:

- 1.) Standard Three (3) Years from date of product installation; or a Five (5) Year Pro-rated Warranty from date of product shipment shall be selected from the certified installer prior to ordering. A default One (1) Year Warranty shall be provided by the contractor directly if no other warranty is selected prior to ordering.

PART 2: PRODUCTS

2.1 Manufacturer:

A.) Unity Surfacing Systems, A Product of Unity Creations, Ltd. 3997 Route 9W (PO Box 9) Saugerties, New York 12477. Toll Free: (1-877) 41-UNITY, Phone (845) 246-2700, Fax: (845) 246-1700, E-mail: productinfo@surfacingystems.com, Internet: www.surfacingystems.com

2.2 Roof (Rubber) Pavers:

A.) Description:

- 1.) Self-Interlocking "Turf-Top" Tile/Mat/Block/Paver size: 22" X 44" = 6.72 sq. ft. per unit (pre-cured). Cured products will measure 21.75" X 43.5" = 6.57 sq. ft. per unit.
- 2.) Transitional Ramp Edge size: 22" X 44" (slope can be found in the 22"). Cured products will measure 21.75" X 43.5" = 6.57 sq. ft. per unit.

B.) Basic Use:

- 1.) Designed for rooftops, walkways, patios, decks, balconies, green roofs, terraces, plazas, roof gardens, etc. It is installed over standard roofing membrane(s) with approval letters from major roofing membrane manufacturers. The product line also features an extensive range of standard ballast tile/mat/block/paver designs and accessory pieces.

C.) Composition and Materials:

- 1.) The Unity, self-interlocking (w/Button-Lock™ Technology), resilient, rubberized safety surfacing flooring and paver products in the "turf-Top" tile/mat/block/paver form offers shock resistance. Comes in Six (6) standard thicknesses and can be produced from 1 ¾" to 4" (4.0") in thickness. Consists of two product families: Post-Consumer Black Recycled SBR (Styrene Butadiene Rubber) and Turf Material.
 - a.) Bottom portion of tiles are produced with 100% post-consumer black recycled SBR (Styrene Butadiene Rubber).
 - b.) Turf Material is comfortable to the touch with anti-microbial additives and antistatic yarns making it look realistic.
 - c.) All of which, are mixed with a polyurethane, molded with heat and pressure and fused together into a homogeneous finished product.
- 2.) Unity offers a solid layer dense construction with bottom designs consisting of solid cones (feet and/or legs) for maximum surface contact offering a built-in self-interlocking system with Button-Lock™ technology. This allows maximum contact between the tile/mat/ block/ paver bottom and base as well as between adjacent products.
- 3.) The type of rooftop playground equipment and/or roof specifications determines the required tile/mat/block/paver thickness. Depending on ASTM F1292-04 requirements for critical fall height from 0'-12' (feet).
 - a.) 1 ¾" (1.75") thick "Pave-Land" series for a five (5') foot fall rating,
 - b.) 2 ½" (2.5") thick "Play-Land" series for a seven (7') foot fall rating,
 - c.) 3" thick Soft-Land" series for an eight (8') foot fall rating,
 - d.) 3 ½" (3.5") thick "Soft-Land" series for a ten (10') foot fall rating,

e.) 4" thick "Soft-Land" series currently testing to achieve a twelve (12') foot fall rating respectively.

4.) Accessories include:

- a.) Unity's Chemrex 948 Urethane Adhesive (Large Tubes) – For gluing interlock-to-interlock adhesion as well as product-to-solid sub-base installations.
- b.) Unity's Transitional Ramp, Standard Beveled Edge – For above grade installations. Slope is standard at 22", but can also be set at 44" for ADA.
- c.) Unity's Geotextile Fabric, Landscaping Mesh – For rooftop installations and loose-filled ground level installation only. **MUST CUT AWAY FROM DRAINS.**

D.) Thickness and Weights:

- 1 ¾" (1.75") thick.~ 34 lbs. each or ~ 5.0 lbs. per sq. ft. (22"X44" only).
- 2" (2.0") thick..... ~ 37 lbs. each or ~ 5.5 lbs. per sq. ft. (22"X44" only).
- 2 ½" (2.50") thick.....~ 40 lbs. each or ~ 6.0 lbs. per sq. ft. (22"X44" only).
- 3" thick.....~ 44 lbs. each or ~ 6.5 lbs. per sq. ft. (22"X44" only).
- 3 ½" (3.5") thick.....~ 47 lbs. each or ~ 7.0 lbs. per sq. ft. (22"X44" only).
- 4" thick.....~ 50 lbs. each or ~ 7.5 lbs. per sq. ft. (22"X44" only).

Note: Adjustments can be made with respect to weight related installations for each item.

Wear Layer for 1 ¾", 2 ½", 3", 3 ½" and 4" thick products to be standard at one (1") inch thick. *22"X44" Tile lines will be visible after installation is complete.

D.) Base Layer: Integral solid cone pedestal design/pattern underside forming channels for water drainage between protective surfacing and substrate to drainage outlet.

F.) Color:

1.) Turf-Top Color:

- a.) Agility, Multi Use, Pet and Playground come in the standard green with a hint of dead grass inside.
- b.) Playground Turf is also available in Blue, Yellow, Red and White for premium price.

G.) Limitations:

- 1.) The following chemicals may cause damage to the rubberized safety surfacing, flooring and paver products, and should be avoided:
 - a.) disinfectants, concentrated chlorine bleach, gasoline, diesel fuel, hydraulic and lubricating oils, acids and organic solvents.
- 2.) In water play areas, pool surrounds and similar applications; dissolved minerals and other chemicals (hydrochlorides) may cause surface discoloration over time. This condition, should it occur, is not considered to be a product failure.
- 3.) Due to the elastic characteristics of recycled rubber products, some variation in dimensions may be expected. Plan for product dimensions of 21¾" X 43½" on items 1 ¾" thick and higher.

- 4.) Turf does in fact get hot in direct sunlight, although it does not retain or radiate much heat. Additionally, we do not guarantee that natural grass/weeds will not grow through the drainage holes. Reflection from windows, highly reflective or shiny surfaces (such as a white PVC fence), or glass top tables can create a magnifying affect and melt the turf. Compression, laying down of fibers, matting and traffic patterns are all considered normal wear and tear.

H.) Testing Data Results on Rubber Tile:

- 1.) Shock Attenuation (ASTM F1292-04 & F355.95):
 - a. G-max – Less than 200 =PASSED.
 - b. Head Injury Criteria – Less than 1000 =PASSED.
 - c. 1 ¾” = 5 foot fall rating, 2 ½” = 7 foot fall rating, 3” = 8 foot fall rating, 3 ½” = 10 foot fall rating and 4” = 11 foot fall rating.

- 2.) Weathering/Aging (ASTM C67, D573 & F1292-04): =.....PASSED.
 - a. 1 ¾” = 5 foot fall rating, 2 ½” = 7 foot fall rating, 3” = 8 foot fall rating, 3 ½” = 10 foot fall rating and 4” = 12 foot fall rating.
 - b. Rubber Deterioration in an Air Over (ASTM D573).....NO DETERIORATION

- 3.) Flammability/Fire Test (ASTM E108).....MEETS “CLASS A” RATING.
 - a. At 1minute 45 seconds the flames traveled four feet along the tip of the sample. At 2 minutes 29 seconds the flames receded to two feet. After 10 minutes of flame exposure at a deck slope of one-quarter in per horizontal foot in 12 mph wind velocity, the burner was shut off. The sample stopped burning 38 seconds after the flame was shut off.

- 4.) Flammability (ASTM E108 Modified for roof covers):.MEETS “CLASS A” RATING
 - a. Ignition Time = 7:24, Maximum Spread of Flame = 40”, Time of Maximum Spread = 8:25. Observations = The Burner Flame was shut off at 10 minutes and the specimen self-extinguished at 13 minutes and 55 seconds, meeting Class A.

- 5.) Flammability (ASTM E648).....MEETS “CLASS I” RATING.
 - a. Each Specimen was laid flat over a ¼” Etera board (a cement asbestos substitute using PC: 96H. Critical Radiant Flux (watts/cm2) averaged = 0.58.

- 6.) Flammability/Burn Pill Test (ASTM2859)..... W/NO OFF GASSING @ 3.7”
 - a. Distance (inches) shall be greater than 1” for all eight test samples to comply.

- 7.) Skid Resistance (ASTM E303-93 / 2013).....PASSED.
 - a. Dry =80.25.
 - b. Wet =67.

- 8.) ADA Accessibility (ASTM F1292-99): =PASSED.
 - a. Firmness =0.26.
 - b. Stability =0.28.

- 9.) R-Value, Thermal Conductivity (ASTM C518-98): =2.4 COMPLIANCE.
 - a. Hot (F) = 96.78, Cold (F) = 50.68, Average = 73.73, Thermal Conductivity Btu-in/hr-ft2-F.

- 10.) Lead In Materials/Children's Products (CPSC-CH-E1002-08):.....NOT DETECTED
a. CPSIA Section 101: Rubber Tile/Mat/Block/Paver: Lead Content (ppm) = ND.
MDL = 2 ppm, Permissible Limit = 300 ppm, Conclusion = Pass.
- 11.) Water Penetration Test (Sustainable Storm Water MGT/Run-off).....VARIES
a. BODY = Penetration is .13 Gallons Per Minute, Per Square Foot of surface area
b. SEAM = Penetration is .21 Gallons Per Minute, Per Square Foot of surface area
- 12.) Leadership in Energy and Environmental Design (LEED):
a. Criteria development by the United States Green Build Council (USGBC):
1.) Materials and Resources:
Up to 6 points / credits toward LEED certification.
Recycled Content.....MR. 4.1
Recycled Content.....MR. 4.2
Local/Regional Materials.....MR 5.1
Local/Regional Materials.....MR 5.2
Construction Waste Mgt.....MR 2.1
Construction Waste Mgt.....MR 2.2
2.) Indoor Environmental Quality:
Up to 1 point / credit toward LEED certification.
Low Emitting Materials.....EQ 4.1
- 13.) Pull Force Test On Solid Sub-Base (ANSI/FM 4474 Approval, App. B)....277.5 psf.
a. Allowable design pressure (2:1 Factor of Safety) for systems installed in the manner described.
- 14.) Wind Resistance (ASTM D3161-09), Over-Top and At Edge Kick-Plate):..150 MPH
a. Over Top = No movement observed after 2 hours continuous exposure.
b. Kick Plate = Lifting observed in center of specimen. Sample remained intact and on roof membrane after 2 hours of continuous exposure.
- 15.) Class 4 Impact Resistance (UL 2218, 2010)PASSED.
a. Six different drop zones observed no damage. No evidence of tearing, fracturing, cracking, splitting, rupturing, crazing, or other evidence of opening of the rubber paver system.
- 16.) Tensile Strength, Elongation at Break and Modulus (ASTM D 412)[MPa] &.[%]
a. Tensile Strength.....0.87 MPa
b. Tensile Strength at Break.....0.76 MPa
c. Elongation.....71.5%
d. Elongation at Break.....92.4%
e. Modulus.....3.49 MPa
- 17.) Tear Resistance (ASTM 624).....[N] &.[kNm]
a. Peak Tearing Load.....156 N
b. Peak Tearing Strength11.3 kNm
- 18.) Taber Abrasion Index (ASTM 624).....0719 WC
- 19.) Durometer Hardness (ASTM 2240).....Shore A = 54

- 20.) Compression Deflection (ASTM 1677).....577 kPa @ 25%
- 21.) Coefficient of Thermal Expansion (ASTM 831).....0013 in/ft. per degree
- 22.) Compression Resistance (ASTM 3574).....[kN] &.[kPa]
 - a. Load at Preset point.....2.78 kN
 - b. Compression Resistance.....1030 kPa
- 23.) Mass & Density (ASTM 3676).....psf & pcf/kg/m³
 - a. Mass Per Area.....2.92 psf
 - b. Density Per Area.....78.8 pcf/1282 kg/m³
 - c. Recovery (D395).....90-100% w/No Cracking
- 24.) Tensile Strength at Interlock Joint (Pull Force To Separate Interlock).....Two Ways.
 - a. Vertical Pull Force Test.....127 PSI or Greater.
 - b. Horizontal Pull Force Test.....38 PSI or Greater.

I.) Testing Data Results on Turf Material:

- 1.) Fiber ID; Melt Point (ASTM D7138).....118-122 Degrees C.
- 2.) Yarn Denier (ASTM D 1577-07).....10,500 – 12,600 Monofilament.
- 3.) Av. Yard Filament Width (ASTM D 3218 07)...Mono = 1,248/Thatch = 715 Microns.
- 4.) Av. Yard Filament Thickness (ASTM D 3218 07)..Mono = 270/Thatch = 126 Microns
- 5.) Total Lead Content Digested by 3052 (ASTM F 2765/EPA 3052, 6010)..< 0.5mg/KG.
- 6.) Av. Weight: Total, Pile Yarn, Prim. and 2nd Backing (ASTM D 5048-10e1) =
 - a.) Total Weight = 55 oz.
 - b.) Pile Yard = 1.2
 - c.) Primary Backing = 6 oz.
 - d.) Secondary Backing = 22 oz.
- 7.) Pile Height (ASTM D 5823-19)....Agility/Multi = 1.0”, Pet = 1.25”, Play55 = 1.2”, 80 = 1.4”
- 8.) Average Stitch Count and Gauge (ASTM D 57930 18).....5.7 Stitches Per Inch / 3/8 Gauge.
- 9.) Average Total Bind Strength (ASTM 1335-17e1).....11.6 lbs of Force.
- 10.) Average Grab Tear (ASTM D 5034-09)....Length = 203, Mid = 225, Width = 58 lbs. @ 5%.
- 11.) Average Pill Flammability (ASTM D 2859-16).....8 of 8 Pass/Meet 16CFR 1630 (F F1-70).
- 12.) Average Abrasive Index (ASTM F 1015-04).....27.
- 13.) Average Drainage Capacity (ASTM F 1551, DIN 18-035).....631 inches/hr.
- 14.) Av. ADA Wheelchair Access. (ASTM F-1951 -14).....Base: 14.81-10.68/Client: 6.85-6.29.

PART 3: EXECUTIONS

3.1 Examinations/Inspections:

A.) Prior to application of the Unity's products, the architect, engineer, municipality, general contractor, safety surfacing manufacturer and installer shall evaluate the roof membranes structural performance. Notify all contactors, architects and engineers of all displacements, leaks or stress cracks. Work shall not proceed until unsatisfactory conditions are corrected and signed by the contractors, architects and engineers; And Unity's installation manual/guide has been read.

3.2 Preparations:

A.) Do not proceed with safety surfacing, flooring and/or paver installation until all applicable site work, including substrate preparation, fascia's, pitch pockets, drains, vent stacks, conduits, roofing and other relevant work, has been fully completed and approved. Verify that roof membrane conditions are suitable for installation of the rubber safety surfacing, flooring and pavers; and do not proceed with installation until unsuitable conditions are corrected, verified and approved.

B.) Roof-edge-to-roof edge installations are encouraged to avoid the use of transitional ramps (edging) as this allow for free-flowing water to the drainage outlet. It is both helpful and advised to plan accordingly when preparing for a counter-sunk installation.

1.) Concrete Sub-base: Shall be as specified in the Division pertaining to the appropriate Section. Apply a light broom finish to "lightly rough" the concrete sub-base. Ensure concrete is sound with no loose materials or cracks over 1/8" (inch) wide in size. Ensure concrete is a minimum of ten (10) days old. Test concrete for any moisture in accordance with manufacturer's installation guide/manual to ensure it has successfully and sufficiently cured and is dry. Existing concrete sub-bases shall be pressure washed and dried in accordance with manufacturer's installation guide/manual.

2.) Roof Membrane Sub-bases: Shall be as specified in the Division pertaining to the appropriate Section. Ensure roof membrane is sound and water tight. Ensure that proper testing of roof membrane has occurred for support, drainage, moisture and/or leaks in accordance with manufacturer's specifications Existing roof membrane sub-bases shall be tested for leaks in accordance with manufacturer's installation guide/manual.

3.) Variations In Elevations of Sub-bases: Shall be relatively even without noticeable high spots or depressions and must be free of accumulated water, ice or snow. Ensure that the pitch of the sub-base material(s) is in accordance with roof membrane manufacturers specifications.


3.3 Installations:

A.) The installation manual / guide shall also be read in full by the General Contract's foreman and all parties of the installation crew.

B.) When installing other products (concrete, wood, composite, etc.) in conjunction with the Unity rubber pavers, the height of the finished area (concrete, wood, composite, etc.) and the rubber pavers being installed shall be flush. This shall be tested every 44" with a full size sample tile/mat/block/paver given to the contractor prior to commencement of installation.

C.) Tiles/mats/blocks/pavers shall be installed on a rectangular configuration of 22” (inches) by 44” (inches) in size [\pm quarter (1/4”) tolerance] with a shadow-center (fake seam) joint to achieve the use of the “step-&repeat” systems to stagger the seams as if you were installing brickwork (zigzag). As a result, symmetry of 22” by 22” squares will be seen on properly completed jobs (installations). Off-setting the joints/seams can also be achieved and shall be approved by the architect of record and the manufacturer, in writing, prior to installation.

D.) Step & Repeat Method of Installation noted below:



E.) For concrete sub-base installations, apply adhesive to the sub-base with a 1/8” notch-trowel. Adhesive consumption will increase as concrete porosity increases.

F.) For recessed installations with a boarding system (concrete, wood, composite, etc.), apply adhesive to the sides of either the edging, or the products themselves at a rate of approximately 40 linear feet per 825 ml tube.

G.) For roof membrane sub-base installations: Apply adhesive to the interlocks, both in the joint (inside wall) and on top of the interlocking joint (outside edge) for added strength and security at a rate of approximately 40 square feet per 825 ml tube. Such application will allow for proper rainwater drainage. **DO NOT GLUE TO ROOF MEMBRANE WHAT-SO-EVER.**

H.) Maintain a straight line at the product joints. To keep lines straight, adjust products using a rubber mallet as they are installed. Apply a string line on the first couple of rows installed to maintain a straight line of installation. Repeat string-line process every so often to make sure you continue a straight line/run of installed products.

I.) All pitch pockets, exposed drains, vent stacks, conduits, protrusions, etc., shall be cut and aligned as required to fit without any gaps. Said cuts, including lead-in cuts, shall be on a 30-degree angle to allow for glue to maintain on the cut unit for added adhesion. Ensure that no cutting is done unless on an elevated platform to allow for clearance and protection of the roofing membrane.

J.) Precautions:

- 1.) The sub-base must be level with a slight pitch for drainage, or uniformly sloped since variations will be telegraphed through to the tile surface. Avoid installation when large temperature swings during the time between adhesive application and final curing (12 - 36 hours, depending on temperature and humidity) are expected, as gapping between tiles/mats/blocks/pavers may result.
- 2.) Protect the newly installed safety surface, flooring and paver material from damage resulting from subsequent construction activity on the site. Temporary applications are possible because products can be loose-laid with interlock-to-interlock gluing, both inside the joint and on top.
- 2.) Remove adhesive (glue) spills from installation area using a clean dry rag and mineral spirits in accordance with manufacturer's installation guide/manual.
- 3.) If applicable, cut geo-textile fabric/landscaping mesh away from any and all drains. Do not cover drains, drain covers, drainage outlets what-so-ever.

3.4 Field Quality Control:

A.) Prior to installation, Contractor shall provide the architect of record and the owner a signed copy of the "Installation Warranty" in writing prior to installation commencement.

B.) Contractor shall "certify" in writing that the sub-base material(s) have been properly compacted, cured and dry as per Section pertaining to Preparations, prior to installation.

C.) Contractor shall "certify" in writing that the "Installation Guide/Manual" has been read by Project Manager and by Lead Installer prior to installation commencement.

D.) Contractor shall "certify" in writing that the flush test (if applicable) has been completed and verified with photographic images sent to the: architect, engineer, municipality, safety surfacing manufacturer.

3.5 Protection:

A.) Protect the installation area from any and all types of subsequent construction and/or foot traffic whether it is human, animal or machine for a minimum of twenty-four (24) hours after installation has occurred.

END OF SECTION 32 18 00 (02791)

Specifiers Notes:

Introduction:

This specification product guide is written according to the Construction Specification Institute (CSI) and the Construction Specifications Canada (CSC) 3-Part Format, MasterFormat, SectionFormat and PageFormat, as described in The Project Resource Manual – CSI Manual of Practice (April 2016 Edition).

The Section(s) must be carefully reviewed and edited by the Architect to meet the requirements of the project and local building code requirements. Coordinate the related Section(s) with other specifications section(s) and the Drawings accordingly. Delete all Specifiers Notes when editing.

1.1 Section Includes:

This covers Unity's Pave-Land, Play-Land, Soft-Land and XL Series of resilient, unitary, rubberized safety surfacing, flooring and paver products in the tile/mat/block/paver form. Contact Unity for assistance in editing any of these Sections for a specific application.

1.2 Related Sections:

Edit the list of related Section(s) as required for the project. List other Section(s) with work directly related to this Section(s).

Include the Section(s) number(s) and title(s) of the Division(s) Section(s), if they are referenced in this section.

1.3 References:

List standards referenced in this Section(s), complete with designation(s) and title(s). This article does not require compliance with standards, as it is merely a listing of those used.

1.8 Warranty Information:

Refer to conditions of the overall Contract for project warranty provisions.

2.1 Manufacturer:

If a local representative is to be the key contact for questions and/or pricing on a local level, their company name, contact person information, address, phone number and e-mail address should be included herein.

2.2 Roof (Rubber) Pavers:

C.) Composition and Materials

3.) Specify thickness(es) of product based on the Critical Fall Height (CFH) and coordinate with working drawings. If not CFH is required, most commonly specified thickness is the 1 ¾" thick Pave-land Series followed by the 2" Play-Land Series.

D.) Thicknesses & Weights

Specify weights and thickness based on the product "Series" selected of each product/unit/series being used. Specify overall size of product being used.

E.) Wear Layer

Specify 1 ¾"-4" thick products at 1" thickness.

*22"X44" Tile lines will be visible after installation is complete.

F. Colors

1.) Specify type and color of Turf Top products on general applications where color(s) are not a primary design consideration.

H.) Testing Data Results

Specify Test Results in accordance with project details accordingly.

a.) 1 ¾" (1.75") thick "Pave-Land" series for a five (5') foot fall rating,

b.) 2 ½" (2.5") thick "Play-Land" series for a seven (7') foot fall rating,

c.) 3" thick Soft-Land" series for an eight (8') foot fall rating,

d.) 3 ½" (3.5") thick "Soft-Land" series for a ten (10') foot fall rating,

Actual test reports, additional testing and additional product information are available upon written request.

3.2 Preparations:

Due to the Porosity of the Unity products, it is essential that a proper sub-base drainage system/run-off be used/constructed or else the products may not stay level and become damaged due to up-lift and/or shifting.

B.3.) Concrete Sub-base – Ensure that adhesive/glue will be used on the sub-base.

B.4.) Roof membrane Sub-base – Ensure that adhesive/glue will be used on the interlocks only, both inside the joint and on top, outside edge.

3.3 Installations:

Rooftop installations often call for adhesive to be applied to the interlocks only. In these cases, do not apply adhesive directly onto the roofing membrane or solid sub-base materials that are temporary without consulting an engineer, architect or end-user. Yield per tube will increase to 80 sq. ft. per tube.